


# Tincture Seeds pigmentation

It 'used to dye cellulosic yarns in shades of light and medium, using dyes in the group (at 50-60 ° C) in the presence of a retarder used to regularize the uniformity of color.

Diagram for yarn dyeing cellulosic seed pigmentation in the medium and light tones.



 **Dye**      **X%**

**Retardant**  **2-3%**

**NaOH**

**Hydrosulphite**